

# SikaGard®-6060

## Sprayable bitumen based underbody coating

### Technical Product Data

Chemical base	Bitumen solution
Colour	Black
Cure mechanism	Air-drying
Density (liquid)	1.1 kg/l approx.
Solid content (DIN 53216)	65% approx.
Application temperature	15 - 25°C
Film thickness	wet dry 600 µm approx. 400 µm approx.
Tack free time <sup>1</sup>	75 min. approx.
Drying time <sup>1</sup>	3.5 h approx.
Service temperature	-25 - 80°C
Shelf life (storage between 5°C and 25°C)	24 months

<sup>1</sup>) 23°C / 50% r.h.

Industry

### Description

SikaGard®-6060 is a durable, thixotropic, bitumen-based protective coating with excellent rust-proofing and sound deadening properties. It is suitable for an effective vehicle underbody protection and convinces with its outstanding application properties and with its excellent final performance.

A tough coating remains after drying, protecting metal from corrosion.

SikaGard®-6060 is manufactured in accordance with ISO 9001/14001 quality assurance system.

### Product Benefits

- Excellent acoustic and damping properties
- Good adhesion performance to a wide variety of substrates
- Outstanding application properties (no running or dripping)
- Road salt resistant
- Fast drying
- High solid content

### Areas of Application

SikaGard®-6060 is a spray applied anti-corrosion coating for repair and protection of non-visible areas such as wheel arches and underbody parts of vehicles that do not need to be over painted.

The product can be sprayed haze free without any cob webbing and does not drip.

SikaGard®-6060 shows good adhesion on different paints, metal primers, metals and PVC without any pre-treatment.

The product is suitable for professional experienced users only. Tests with actual substrates and conditions have to be performed to ensure adhesion and material compatibility.



### Chemical Resistance

SikaGard®-6060 is resistant against water, seawater, salt spray, bases and acids.

The above information is offered for general guidance only. Advice on specific applications will be given on request.

### Method of Application

#### Surface preparation

Surfaces must be clean, dry and free of rust, dust and grease. Bare metal must be pre-treated to enhance corrosion resistance (e.g. uncoated steel, etc).

#### Application

SikaGard®-6060 can be applied by light airless spray equipments or by air-mix guns with an air pressure of approx. 3 - 6 bar. Use either the Sika® SCP Gun (pressure cup type) or the Sika® UBC Gun (vacuum type) to apply the product.

Shake can approx. 40 times before use. Cover adjacent surfaces prior the spray process. Spray at room temperature and from a distance of approx. 25 cm in an X motion to build up a continuous coat. SikaGard®-6060 can be applied without dripping. If a thick layer is required, let layers dry in between. A wide variety of texture can be achieved by altering the spray technique.

Do not spray on parts of the brake, engine or exhaust system.

### Removal

Fresh SikaGard®-6060 can be removed from tools and equipment with Sika® Remover-208. Once dried, the material can only be removed mechanically.

Hands and exposed skin should be washed immediately using Sika® Handclean towels or a suitable industrial hand cleaner and water. Do not use solvents!

### Over painting

SikaGard®-6060 is not over paintable.

### Further Information

Copies of the following publication is available on request:

- Safety Data Sheet

### Packaging Information

Can	1 l
Jerry can	10 l
Drum	60 l

### Value Basis

All technical data stated in this Product Data Sheet is based on laboratory tests. Actual measured data may vary due to circumstances beyond our control.

### Health and Safety Information

For information and advice regarding transportation, handling, storage and disposal of chemical products, users shall refer to the actual Material Safety Data Sheets containing physical, ecological, toxicological and other safety-related data.

### Legal Notes

The information, and, in particular, the recommendations relating to the application and end-use of Sika products, are given in good faith based on Sika's current knowledge and experience of the products when properly stored, handled and applied under normal conditions in accordance with Sika's recommendations. In practice, the differences in materials, substrates and actual site conditions are such that no warranty in respect of merchantability or of fitness for a particular purpose, nor any liability arising out of any legal relationship whatsoever, can be inferred either from this information, or from any written recommendations, or from any other advice offered. The user of the product must test the product's suitability for the intended application and purpose. Sika reserves the right to change the properties of its products. The proprietary rights of third parties must be observed. All orders are accepted subject to our current terms of sale and delivery. Users must always refer to the most recent issue of the local Product Data Sheet for the product concerned, copies of which will be supplied on request.

Further information available at:

[www.sika.ch](http://www.sika.ch)  
[www.sika.com](http://www.sika.com)

Sika Schweiz AG  
Business Unit Industry  
Tüffenwies 16  
CH-8048 Zurich  
Switzerland  
Tel. +41 58 436 40 40  
Fax +41 58 436 45 30

